

EWI-075 SILICONE RENDER PRODUCT DATA SHEET

EWI-075 Silicone Render is a ready-to-use, through-coloured decorative render designed to provide a durable, flexible and highly breathable finish for external walls. Its silicone-based formulation provides good resistance to mechanical impact and UV exposure, while its hydrophobic properties help reduce water absorption and support long-term weather resistance.



Intended Uses

EWI-075 Silicone Render is intended for use as a decorative finish over suitably prepared reinforced basecoat layers in render-only and external wall insulation systems. It can be applied by hand or suitable spray equipment and is available in a range of grain sizes.

Technical Specification

Composition

Silicone emulsions, acrylic polymer dispersion, fillers, modifying admixtures and pigments

Quantity Per Unit

25kg

Grain Size

0.5mm, 1mm, 1.5mm, 2mm or 3mm

Consumption

0.5mm: approx. 1.6kg/m², 1.0mm: approx. 1.9kg/m², 1.5mm: approx. 2.4kg/m², 2.0mm: approx. 3.4kg/m², 3.0mm: approx. 5.0kg/m²

Application Thickness

Apply at the selected grain size

Recommended Thickness

Apply at the selected grain size

Coverage Rate

0.5mm: approx. 16–20m² per 25kg, 1.0mm: approx. 12–13m² per 25kg, 1.5mm: approx. 9–10m² per 25kg, 2.0mm: approx. 6–8m² per 25kg, 3.0mm: approx. 5–6m² per 25kg

Dry Bulk Density

Approx. 1.84g/cm³

Application Temperature

+5°C to +25°C

Drying Time

Approx. 12–48 hours

Relative Diffusion Resistance

≤ 0.13m

Water Vapour Permeability

<1.00m

Water Absorption

<0.5kg/m²

Organic Content

6.37%

Adhesion after Ageing – Mineral Wool

≤ 0.08MPa

Adhesion after Ageing – EPS

≤ 0.003MPa

Reaction to Fire – Mineral Wool System

Class A2

Reaction to Fire – EPS System

Class B

Please note: Thickness, consumption, coverage and time figures are indicative only and may vary depending on the substrate, application method and site conditions.

Please see the reverse of this page for directions for use.

Directions for use

Substrate Preparation

The substrate must be sound, stable, dry and free from dust, dirt, loose material and other contaminants that may affect adhesion. The reinforced basecoat should be fully cured and appropriately prepared before application. Where required, use a suitable primer according to the substrate type, condition and absorbency.

Product Preparation

EWI-075 Silicone Render is supplied ready to use and should not be diluted with water or mixed with other products. Before application, mix thoroughly to achieve an even consistency and check that the colour matches the order. Where multiple tubs are required on the same elevation, material should be blended during application to help maintain colour consistency.

Application

For 1mm, 1.5mm, 2mm and 3mm grain sizes, apply EWI-075 evenly using a stainless steel trowel and remove excess material until the applied thickness matches the selected grain size. Immediately texture the surface using a plastic render float in circular motions to produce a consistent finish.

For 0.5mm render, apply two thin passes at approximately 0.5mm per pass. Allow the first pass to dry fully before applying the second. Once the second pass begins to firm, finish the surface using a plastic render float.

Work continuously across each elevation where possible and avoid allowing individual sections to dry before adjoining areas are completed.

Application Conditions

Apply between +5°C and +25°C. Protect freshly applied render from rain, frost, strong winds, direct sunlight and rapid drying. Drying time is typically 12–48 hours but may be longer in low temperatures or unfavourable site conditions.

Clean-up

Clean tools and equipment with clean water immediately after use. Do not allow material to dry onto tools and do not dispose of waste material into drainage systems.

Packaging & Storage

Supplied in 25kg tubs. Store unopened in a dry environment at temperatures above +5°C and protect from frost and extreme temperatures. Shelf life is up to 12 months from the date of manufacture when stored correctly.

Address:

Unit 1-2 King George's Trading Estate,
Davis Road,
Chessington,
England,
KT9 1TT

Email:

info@ewipro.com

Phone:

0800 133 7072



EWIPRO

Compliance with Standards

PN-C-81913:1998.
ETA 15/0576 and ETA 15/0575.
BBA Approval Inspection Testing Certificate
18/5503.

Safety Measures

Wear suitable protective gloves, protective clothing and eye protection during application. Avoid contact with the skin and eyes. In the event of eye contact, rinse immediately with plenty of clean water and seek medical advice where necessary. Refer to the relevant Safety Data Sheet for full handling, first aid and disposal information.

General Information

This data sheet replaces all previous editions. The information provided is based on current knowledge and practical experience, and while it has been compiled with care, it is not guaranteed to be accurate, complete or suitable for all applications. It is the responsibility of the user to verify the product's suitability for their specific use case. No legal obligations are established by this document.

Data Sheet Revision Date: 28/10/2026



www.ewipro.com